

# Everlube® Products

National Customer Service Toll-free Phone 1-800-428-7802 • 1-770-261-4800

## TECHNICAL DATA

PEK1201

### EVER-SLIK® 1201 Basecoat / Barrier Coating

#### Product Description:

- Solvent based epoxy system
- Thermally cured coating
- Extreme toughness, flexibility and durability
- Outstanding chemical resistance
- Superior Corrosion Resistance
- Inherent hydrophobic properties allows coating to repel water and other process fluids.

#### Typical Uses:

- Valves and fittings used in the petrochemical industry.
- Functional components used in the offshore drilling industry.
- To enhance corrosion resistance properties when used as a primer under solid film lubricants (such as Everslik® 1301).

#### Typical Physical Properties:

Color and appearance*	Glossy black or "primer" red finish. Other colors are available on a special order basis.
Solids content (by weight)*	43 to 47%
Solids content (by volume)	32 to 36%
Density*	8.4 ± 0.5 lb/gal (1006 ± 60 grams/liter)
Theoretical coverage	545 sq. ft./gallon @ 1.0 mils (13.3 sq. meters/ltr @25.4 microns)
Volatile organic compound (V.O.C.)	580 grams/liter
Pencil Hardness	>4H
Operating temperature range	-100° to 400°F (-73° to 204°C)
Shelf Life	1 year from date of manufacture, stored in a factory sealed container at 40° to 100°F. Shipped with a minimum of 75% shelf life.

#### Recommended Application Procedure:

Application Method:	Spray
Dilution Ratio (by volume):	1:1 to 1:3 (product:solvent)
Dilution and Clean-up Solvent:	1201 solvent or 80%MEK/20% NMP
Application Sequence:	Apply the Everslik 1201 in at least 3 thin coats of 0.0002" to 0.0003" (5 to 7 microns) dry film thickness per coat. Allow to air dry for at least 15 minutes between coats.

(Continued)

This document is not intended for use as a specification. Specification writers should contact Technical Director of Research and Development. This information supplied is presented in good faith and has been derived from sources believed to be reliable. Since conditions of use are beyond our control, all risks are assumed by the user. No representation or warranty is expressed or implied and all warranties including warranties of marketability and fitness for use are expressly disclaimed. Nothing herein shall be construed as permission or recommendation to practice a patented invention without a license.

**Cure cycle:**

As a primer: Flash cure the Everslik 1201 at 200° to 250° (93° to 121°C) for 20 to 40 minutes. Let cool to room temperature before applying the topcoat. The final cure is 350° to 400°F. (177° to 204°C) for 1 hour (+15, -0 min.) (part metal temperature).

As a barrier coating: 350° to 400°F (177° to 204°C) for 1 hour (+15, -0 min.) (part metal temperature).

For addition information see Application Bulletin #3000-A

**Typical Functional Properties (for reference use only)**

Adhesion (ASTM D-3359)	Pass
Thermal stability (ASTM D-2511)	Pass
Taber abraser (ASTM D-4060)	(25 microns)
CS-17 wheels, 1 kg load	<0.001" coating thickness wear per 2500 cycles
CS-10 wheel, 1 kg load	<18 mg weight loss/1000 cycles

Neutral Salt Spray Corrosion resistance  
(ASTM B-117) @0.0012" (30.5 microns)  
on Mn. phosphated 1010 CRS steel  
test panels >2500 hours to failure

Sulfurous Acid Corrosion Resistance  
(ASTM G-85) @0.0012" (30.5 microns)  
on Mn. phosphated 1010 CRS steel  
test panels. >2500 hours to failure

**Chemical Resistance:**

100 hours immersion Ambient temperature

- Anodized aluminum panels  
Fluid  
Skydrol 500A No effect  
Trichloroethylene No effect  
Methylene Chloride No effect  
Hydrochloric Acid (15%) No effect  
Sulfuric Acid (50%) No effect  
Nitric Acid (10%) No effect
- Steel panel  
Fluid  
Sodium Hydroxide (25%) No effect

\* Lot Tests